


Amendments to the Claims

The listing of claims presented below replaces all prior versions, and listings, of claims in the application.

Listing of claims:

1. (currently amended) A volume hologram recording photosensitive composition, comprising a fluorine-contained photoreactive compound represented by the following formula (1) and a binder resin:

Formula (1)




wherein each R^1 and R^2 in the formula (1) is independently an epoxy group or an oxetanyl group ~~are photoreactive groups which can be bonded to each other by photoreaction~~, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms, and n is an integer of 1 or more.

2-4. (cancelled)

5. (currently amended) The volume hologram recording photosensitive composition according to claim 1 [[4]], wherein each of R^1 and R^2 is an epoxy group.

6. (currently amended) The volume hologram recording photosensitive composition according to claim 1 [[4]], wherein each of R^1 and R^2 in the formula (1) is an oxetanyl group represented by the following formula (2):

Formula (2)



wherein R^5 is a hydrogen atom or an alkyl group having 1 to 10 carbon atoms.

7. (original) The volume hologram recording photosensitive composition

according to claim 1, wherein each of R³ and R⁴ in the formula (1) is independently a single bond or a linear hydrocarbon group.

8. (original) The volume hologram recording photosensitive composition according to claim 1, which further comprises a photopolymerization initiator.

9. (cancelled)

10. (currently amended) The volume hologram recording photosensitive composition according to claim 1 [[9]], wherein the binder resin comprises at least one selected from the group consisting of a thermoplastic resin, a thermosetting resin, an organic-inorganic hybrid polymer, and an organic metal compound represented by the formula (4):

Formula (4)

$M'(OR'')^{n'}$

wherein M' represents a metal such as Ti, Zr, Zn, In, Sn, Al or Se, and R'' represents an alkyl group having 1 to 10 carbon atoms, and n' is the valence number of the metal M'.

11. (original) The volume hologram recording photosensitive composition according to claim 1, which further comprises a second refractive index modulating component other than the fluorine-contained photoreactive compound.

12. (original) The volume hologram recording photosensitive composition according to claim 11, wherein a combination of ingredients for forming a refractive index difference is any one selected from the group consisting of the following (1) to (4):

(1) a combination comprising the fluorine-contained photosensitive compound represented by the formula (1), a binder resin having a refractive index different from that of the fluorine-contained photosensitive compound, and a radical photopolymerizable compound which is the second refractive index modulating

component having a refractive index different from that of the fluorine-contained photosensitive compound;

(2) a combination comprising the fluorine-contained photosensitive compound represented by the formula (1), a binder resin having a refractive index different from that of the fluorine-contained photosensitive compound, and a cationic photopolymerizable compound which is the second refractive index modulating component having a refractive index different from that of the fluorine-contained photosensitive compound;

(3) a combination comprising the fluorine-contained photosensitive compound represented by the formula (1), and two or more radical photopolymerizable compounds which are the second refractive index modulating components each having a refractive index different from that of the fluorine-contained photosensitive compound; and

(4) a combination comprising the fluorine-contained photosensitive compound represented by the formula (1), a radical photopolymerizable compound which is the second refractive index modulating component having a refractive index different from that of the fluorine-contained photosensitive compound, and a cationic photopolymerizable compound which is the second refractive index modulating component having a refractive index different from that of the fluorine-contained photosensitive compound.

13. (original) The volume hologram recording photosensitive composition according to claim 1, which further comprises metal fine particles having a refractive index different from that of the fluorine-contained photosensitive compound represented by the formula (1).


14. (original) The volume hologram recording photosensitive composition according to claim 1, which further comprises a sensitizing dye which gets transparent by light-exposure or treatment after the light-exposure.

15. (original) The volume hologram recording photosensitive composition according to claim 14, wherein the sensitizing dye is at least one selected from the group consisting of cyanine type dyes, merocyanine type dyes, coumalin type dyes,

ketocoumalin type dyes, and cyclopentanone type dyes.

16. (currently amended) A volume hologram recording photosensitive medium, having a hologram recording section made of a volume hologram recording photosensitive composition comprising a fluorine-contained photoreactive compound represented by the following formula (1) and a binder resin:


Formula (1)



wherein R^1 and R^2 in the formula (1) is independently an epoxy group or an oxetanyl group ~~are photoreactive groups which can be bonded to each other by photoreaction~~, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms, and n is an integer of 1 or more.

17. (currently amended) A volume hologram having a hologram layer, wherein the hologram layer is formed by exposing, to light, a volume hologram recording photosensitive medium having a hologram recording section made of a volume hologram recording photosensitive composition comprising a fluorine-contained photoreactive compound represented by the following formula (1) and a binder resin:

Formula (1)




wherein R^1 and R^2 in the formula (1) is independently an epoxy group or an oxetanyl group ~~are photoreactive groups which can be bonded to each other by photoreaction~~, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms and n is an integer of 1 or more, at the hologram recording section, and

wherein the hologram layer has 0.016 or more of refractive index modulation (Δn) between its low refractive index region and its high refractive index region.

18. (new) A volume hologram recording photosensitive composition, comprising a

fluorine-contained photoreactive compound represented by the following formula (1) and metal fine particles having a refractive index different from that of the fluorine-contained photosensitive compound represented by the formula (1):

Formula (1)



wherein R^1 and R^2 in the formula (1) is independently an acryloyl group or a methacryloyl group and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms, and n is an integer of 1 or more.

19. (new) The volume hologram recording photosensitive composition according to claim 18, which further comprises a photopolymerization initiator.
20. (new) The volume hologram recording photosensitive composition according to claim 18, which further comprises a binder resin.
21. (new) The volume hologram recording photosensitive composition according to claim 20, wherein the binder resin comprises at least one selected from the group consisting of a thermoplastic resin, a thermosetting resin, an organic-inorganic hybrid polymer, and an organic metal compound represented by the formula (4):

Formula (4)




wherein M' represents a metal such as Ti, Zr, Zn, In, Sn, Al or Se, and R'' represents an alkyl group having 1 to 10 carbon atoms, and n' is the valence number of the metal M' .

22. (new) The volume hologram recording photosensitive composition according to claim 18, which further comprises a sensitizing dye which is at least one member selected from the group consisting of cyanine type dyes, merocyanine type dyes,

coumalin type dyes, ketocoumalin type dyes, and cyclopentanone type dyes.

23. (new) A volume hologram recording photosensitive medium, having a hologram recording section made of a volume hologram recording photosensitive composition comprising a fluorine-contained photoreactive compound represented by the following formula (1) and metal fine particles having a refractive index different from that of the fluorine-contained photosensitive compound represented by the formula (1):


Formula (1)



wherein each R^1 and R^2 in the formula (1) is independently an acryloyl group or a methacryloyl group, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms, and n is an integer of 1 or more.

24. (new) A volume hologram having a hologram layer, wherein the hologram layer is formed by exposing, to light, a volume hologram recording photosensitive medium having a hologram recording section made of a volume hologram recording photosensitive composition comprising a fluorine-contained photoreactive compound represented by the following formula (1) and metal fine particles having a refractive index different from that of the fluorine-contained photosensitive compound represented by the formula (1):

Formula (1)




wherein each R^1 and R^2 in the formula (1) is independently an acryloyl group or a methacryloyl group, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms, and n is an integer of 1 or more, at the hologram recording section, and

wherein the hologram layer has 0.016 or more of refractive index modulation (Δn) between its low refractive index region and its high refractive index region.

25. (new) A volume hologram recording photosensitive composition, comprising a fluorine-contained photoreactive compound represented by the following formula (1) and a binder resin which is at least one member selected from the group consisting of a vinyl acetate-acrylic copolymer resin, an epoxy group-contained acrylic resin, an oligomer type setting resin, and an organic-inorganic hybrid resin:

Formula (1)



wherein each R^1 and R^2 in the formula (1) is independently an acryloyl group or a methacryloyl group, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms, and n is an integer of 1 or more.


26. (new) The volume hologram recording photosensitive composition according to claim 25, which further comprises a radical photopolymerizable compound which is the second refractive index modulating component having a refractive index different from that of the fluorine-contained photosensitive compound represented by formula (1), and/or a cationic photopolymerizable compound which is the second refractive index modulating component having a refractive index different from the fluorine-contained photosensitive compound represented by formula (1).

27. (new) The volume hologram recording photosensitive composition according to claim 25, which further comprises a sensitizing dye which is at least one member selected from the group consisting of cyanine type dyes, merocyanine type dyes, coumalin type dyes, ketocoumalin type dyes, and cyclopentanone type dyes.

28. (new) A volume hologram recording photosensitive medium, having a hologram recording photosensitive composition comprising a fluorine-contained photoreactive compound represented by the following formula (1) and a binder resin

which is at least one member selected from the group consisting of a vinyl acetate-acrylic copolymer resin, an epoxy group-contained acrylic resin, an oligomer type setting resin, and an organic-inorganic hybrid resin:


Formula (1)



wherein each R^1 and R^2 in the formula (1) is independently an acryloyl group or a methacryloyl group, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms, and n is an integer of 1 or more.

29. (new) A volume hologram having a hologram layer, wherein the hologram layer is formed by exposing, to light, a volume hologram recording photosensitive medium having a hologram recording section made of a volume hologram recording photosensitive composition comprising a fluorine-contained photoreactive compound represented by the following formula (1) and a binder resin which is at least one member selected from the group consisting of a vinyl acetate-acrylic copolymer resin, an epoxy group-contained acrylic resin, an oligomer type setting resin, and an organic-inorganic hybrid resin:

Formula (1)



wherein R^1 and R^2 in the formula (1) is independently an acryloyl group or a methacryloyl group, and each of R^3 and R^4 is independently a single bond or a bivalent hydrocarbon group having 1 to 5 carbon atoms and n is an integer of 1 or more, at the hologram recording section, and

wherein the hologram layer has 0.016 or more of refractive index modulation (Δn) between its low refractive index region and its high refractive index region.